

Test report n°: 20LA07546 of 25/06/2020





LAB N° 1165 L

Dear **Spandex Ltd** 1600 Park Avenue Aztec West BS32 4UA Bristol ()

Acceptance Data Subject of the test: Polymers Transport: Customer Date of arrival: 22/05/2020 Time of arrival: 15.23 Acceptance date: 22/05/2020

### Sample data

Description: ImagePerfect, SafeTouch post 50 washing ethanol 70%

#### Sampling data

Sampling by: Customer Place: Customer location

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







#### Test report n°: **20LA07546** of **25/06/2020**

Parameter - Specification Method - Notes	M.U.	Results Notes	LoQ	LoD Test start Test end
Determination of antibacterial activity (R) - R=(Ut-Uo)-(At- Uo) ISO 22196:2011		> 4.5	0,3	16/06/2020 19/06/2020
Determination of antibacterial activity (R) ISO 22196:2011	%	> 99.997	50	16/06/2020 19/06/2020
Size of test specimens (H x L)	mm	50x50		16/06/2020 19/06/2020
Thickness of test specimens	mm	0,1		16/06/2020 19/06/2020
Type of polymer used for the cover film		Polypropylene		16/06/2020 19/06/2020
Size of the cover film (H x L)	mm	40x40		16/06/2020 19/06/2020
Thickness of the cover film	mm	0,10		16/06/2020 19/06/2020
Type of Gram-positive strain		Staphylococcus aureus - ATCC 6538		16/06/2020 19/06/2020
Method of conditioning		UV-C radiation (30 min per side)		16/06/2020 19/06/2020
Reference used		Inert Internal material		16/06/2020 19/06/2020
Volume of test inoculum	ml	0,4		16/06/2020 19/06/2020
Number of viable bacteria in the test inoculum	n°	350000		16/06/2020 19/06/2020
Uo - N° of viable bacteria recovered from the untreated test specimens after inoculation	log	4,3	0,4	16/06/2020 19/06/2020
Ut - N° of viable bacteria recovered from the untreated test specimens after 24 h	log	4,5	0,4	16/06/2020 19/06/2020
At - Count bacteria recovered from the treated samples 24 hours post inoculation	log	NQ	0,4	16/06/2020 19/06/2020

If the sampling is not the responsibility of 3ALaboratori srl, the latter declines all responsibility with regard to sampling information as provided by the Customer; the test results refer only to the sample as received. When these data include measurements that affect the measurement unit, the results expressed are obtained by processing them. The Acceptance Data is the responsibility of the Laboratory while the sample data are the responsibility of the Customer. If the sample is not suitable but the Customer chooses to continue anyway, the laboratory declines all responsibility for the results that could be influenced by the deviation

LEGEND: U.M. = Unit of measurement; (Sup) = upper limit; (Inf) = Lower Limit ; LoQ = limit of quantification, it is the lower limit of concentration above which it is possible to obtain a quantitative measurement instrumentally; in microbiology the LoQ is of a theoretical nature; LoD = limit of detectability, is the lower limit of concentration below which the sample cannot be detected; in qualitative analyzes it represents the minimum concentration at which an analyte can be determined or not; NQ = unquantifiable, indicates a value less than LoQ; NR = not detectable, indicates a value lower than LoD;"<x" or ">x" respectively indicate a value lower or higher than the measuring range of the test, where x is the result

(§): Indicates a change from the previous version of the Test Report.

(le): Indicates that the parameters/activities are performed in subcontracting.

UNLESS OTHERWISE SPECIFIED: Quantitative microbiological tests are performed on single replica and two consecutive dilutions in accordance with UNI EN ISO 7218: 2013 (with the exception of the analysis of water and MPN); the results of this test report are not corrected for recovery factors (R) as the values of recovery are in the tolerance

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







### Test report n°: 20LA07546 of 25/06/2020

specified in the test method; summations are calculated using the criterion of the lower bound (LB)

(\*): Test/activity not accredited by ACCREDIA

# Notes:

Washing method: immersion of the specimen in 70% ethanol (room temperature 18-25 ° C) for 1 minute followed by drying phase by tamponing with disposable paper.

Washing is repeated 50 times. Rinse with running water for 5 minutes before testing.

**Technical Director** 

Dr. Giovanni Mitaritonna Chemist Ordine Interprov. Chimici del Veneto - Padova nº 910 SEZ. A

----- End of Test Report

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.
Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge
Mod.PT01.01 Rev.9 Mod.PT01.01 Rev.9



Test report n°: 20LA07547 of 25/06/2020





LAB N° 1165 L

Dear **Spandex Ltd** 1600 Park Avenue Aztec West BS32 4UA Bristol ()

Acceptance Data Subject of the test: Polymers Transport: Customer Date of arrival: 22/05/2020 Time of arrival: 14.06 Acceptance date: 22/05/2020

### Sample data

Description: ImagePerfect, SafeTouch post 50 washing sodium hypochlorite 0.1%

#### Sampling data

Sampling by: Customer Place: Customer location

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







#### Test report n°: **20LA07547** of **25/06/2020**

Parameter - Specification Method - Notes	M.U.	Results Notes	LoQ	LoD Test start Test end
Determination of antibacterial activity (R) - R=(Ut-Uo)-(At- Uo) ISO 22196:2011		> 4.5	0,3	16/06/202 19/06/202
Determination of antibacterial activity (R) ISO 22196:2011	%	> 99.997	50	16/06/202 19/06/202
Size of test specimens (H x L)	mm	50x50		16/06/202 19/06/202
Thickness of test specimens	mm	0,1		16/06/202 19/06/202
Type of polymer used for the cover film		Polypropylene		16/06/202 19/06/202
Size of the cover film (H x L)	mm	40x40		16/06/202 19/06/202
Thickness of the cover film	mm	0,10		16/06/202 19/06/202
Type of Gram-positive strain		Staphylococcus aureus - ATCC 6538		16/06/202 19/06/202
Method of conditioning		UV-C radiation (30 min per side)		16/06/202 19/06/202
Reference used		Inert Internal material		16/06/202 19/06/202
Volume of test inoculum	ml	0,4		16/06/202 19/06/202
Number of viable bacteria in the test inoculum	n°	350000		16/06/202 19/06/202
Uo - N° of viable bacteria recovered from the untreated test specimens after inoculation	log	4,3	0,4	16/06/202 19/06/202
Ut - $N^\circ$ of viable bacteria recovered from the untreated test specimens after 24 h	log	4,5	0,4	16/06/202 19/06/202
At - Count bacteria recovered from the treated samples 24 hours post inoculation	log	NQ	0,4	16/06/202 19/06/202

If the sampling is not the responsibility of 3ALaboratori srl, the latter declines all responsibility with regard to sampling information as provided by the Customer; the test results refer only to the sample as received. When these data include measurements that affect the measurement unit, the results expressed are obtained by processing them. The Acceptance Data is the responsibility of the Laboratory while the sample data are the responsibility of the Customer. If the sample is not suitable but the Customer chooses to continue anyway, the laboratory declines all responsibility for the results that could be influenced by the deviation

LEGEND: U.M. = Unit of measurement; (Sup) = upper limit; (Inf) = Lower Limit ; LoQ = limit of quantification, it is the lower limit of concentration above which it is possible to obtain a quantitative measurement instrumentally; in microbiology the LoQ is of a theoretical nature; LoD = limit of detectability, is the lower limit of concentration below which the sample cannot be detected; in qualitative analyzes it represents the minimum concentration at which an analyte can be determined or not; NQ = unquantifiable, indicates a value less than LoQ; NR = not detectable, indicates a value lower than LoD;"<x" or ">x" respectively indicate a value lower or higher than the measuring range of the test, where x is the result

(§): Indicates a change from the previous version of the Test Report.

(le): Indicates that the parameters/activities are performed in subcontracting.

UNLESS OTHERWISE SPECIFIED: Quantitative microbiological tests are performed on single replica and two consecutive dilutions in accordance with UNI EN ISO 7218: 2013 (with the exception of the analysis of water and MPN); the results of this test report are not corrected for recovery factors (R) as the values of recovery are in the tolerance

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







### Test report n°: **20LA07547** of **25/06/2020**

specified in the test method; summations are calculated using the criterion of the lower bound (LB)

(\*): Test/activity not accredited by ACCREDIA

## Notes:

Washing method: immersion of the specimen in Sodium hypochlorite (bleach) at 0.1% (room temperature 18-25 ° C) for 1 minute followed by drying phase by tamponing with disposable paper. Washing is repeated 50 times. Rinse with running water for 5 minutes before testing.

**Technical Director** 

Dr. Giovanni Mitaritonna Chemist Ordine Interprov. Chimici del Veneto - Padova nº 910 SEZ. A

------ End of Test Report ------

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.
Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge
Mod.PT01.01 Rev.9



Test report n°: 20LA07548 of 25/06/2020





LAB N° 1165 L

Dear **Spandex Ltd** 1600 Park Avenue Aztec West BS32 4UA Bristol ()

Acceptance Data Subject of the test: Polymers Transport: Customer Date of arrival: 22/05/2020 Time of arrival: 14.07 Acceptance date: 22/05/2020

## Sample data

Description: ImagePerfect, SafeTouch post 50 washing Benzalkonium chloride 5% (GD90)

#### Sampling data

Sampling by: Customer Place: Customer location

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







#### Test report n°: 20LA07548 of 25/06/2020

Parameter - Specification Method - Notes	M.U.	Results Notes	LoQ	LoD Test start Test end
Determination of antibacterial activity (R) - R=(Ut-Uo)-(At- Uo) ISO 22196:2011		> 4.5	0,3	16/06/2020 19/06/2020
Determination of antibacterial activity (R) ISO 22196:2011	%	> 99.997	50	16/06/2020 19/06/2020
Size of test specimens (H x L)	mm	50x50		16/06/2020 19/06/2020
Thickness of test specimens	mm	0,1		16/06/2020 19/06/2020
Type of polymer used for the cover film		Polypropylene		16/06/2020 19/06/2020
Size of the cover film (H x L)	mm	40x40		16/06/2020 19/06/2020
Thickness of the cover film	mm	0,10		16/06/2020 19/06/2020
Type of Gram-positive strain		Staphylococcus aureus - ATCC 6538		16/06/2020 19/06/2020
Method of conditioning		UV-C radiation (30 min per side)		16/06/2020 19/06/2020
Reference used		Inert Internal material		16/06/2020 19/06/2020
Volume of test inoculum	ml	0,4		16/06/2020 19/06/2020
Number of viable bacteria in the test inoculum	n°	350000		16/06/2020 19/06/2020
Uo - N° of viable bacteria recovered from the untreated test specimens after inoculation	log	4,3	0,4	16/06/2020 19/06/2020
Ut - $N^\circ$ of viable bacteria recovered from the untreated test specimens after 24 h	log	4,5	0,4	16/06/2020 19/06/2020
At - Count bacteria recovered from the treated samples 24 hours post inoculation	log	NQ	0,4	16/06/2020 19/06/2020

If the sampling is not the responsibility of 3ALaboratori srl, the latter declines all responsibility with regard to sampling information as provided by the Customer; the test results refer only to the sample as received. When these data include measurements that affect the measurement unit, the results expressed are obtained by processing them. The Acceptance Data is the responsibility of the Laboratory while the sample data are the responsibility of the Customer. If the sample is not suitable but the Customer chooses to continue anyway, the laboratory declines all responsibility for the results that could be influenced by the deviation

LEGEND: U.M. = Unit of measurement; (Sup) = upper limit; (Inf) = Lower Limit ; LoQ = limit of quantification, it is the lower limit of concentration above which it is possible to obtain a quantitative measurement instrumentally; in microbiology the LoQ is of a theoretical nature; LoD = limit of detectability, is the lower limit of concentration below which the sample cannot be detected; in qualitative analyzes it represents the minimum concentration at which an analyte can be determined or not; NQ = unquantifiable, indicates a value less than LoQ; NR = not detectable, indicates a value lower than LoD;"<x" or ">x" respectively indicate a value lower or higher than the measuring range of the test, where x is the result

(§): Indicates a change from the previous version of the Test Report.

(le): Indicates that the parameters/activities are performed in subcontracting.

UNLESS OTHERWISE SPECIFIED: Quantitative microbiological tests are performed on single replica and two consecutive dilutions in accordance with UNI EN ISO 7218: 2013 (with the exception of the analysis of water and MPN); the results of this test report are not corrected for recovery factors (R) as the values of recovery are in the tolerance

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.







### Test report n°: 20LA07548 of 25/06/2020

specified in the test method; summations are calculated using the criterion of the lower bound (LB)

(\*): Test/activity not accredited by ACCREDIA

## Notes:

Washing method: immersion of the specimen in Benzalkonium chloride at 5% - GD90 (room temperature 18-25 ° C) for 1 minute followed by drying phase by tamponing with disposable paper. Washing is repeated 50 times. Rinse with running water for 5 minutes before testing.

**Technical Director** 

Dr. Giovanni Mitaritonna Chemist Ordine Interprov. Chimici del Veneto - Padova nº 910 SEZ. A

----- End of Test Report

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.
Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge
Mod.PT01.01 Rev.9