

P.S. METALLIC

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	& Certifications		
PU	100 microns	Adhesive polyester	REACH n° 1907/2006/EU VEGANOK AZIENDA N. 1004		

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/ cotton blends (not suited for treated	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
`and dye sublimated textiles)	60°	130 gf	15 cm/sec	15 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	cold

- → Cut the material mirrored
- → Peel off excess material
- → Place the decoration on the garment
- → Apply following the recommended parameters
- ightarrow Remove the carrier when cold

PRODUCT HIGHLIGHTS

- → Metallic effect
- → Glossy almost mirrored like finish
 - NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Handwash	YES best inside-out	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



