

AUTO Wrap 1D - Laminate



The AUTO brand, exclusively from Spandex, is designed to cater for the ever-changing needs of professional wrappers, detailers and fleet applicators. The products are co-branded and have been developed in conjunction with leading manufacturers. AUTO offers a range of special edition automotive colours, paint protection films, digital wrap bundles, automotive tint films and accessories. The AUTO Wrap range has been manufactured by Arlon exclusively for Spandex.

PRODUCT DESCRIPTION

AUTO Wrap 1D Laminate is a 80 microns polymeric vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect and prolong the life of printed images, AUTO Wrap 1D Laminate is made of a polymeric facestock and available in gloss and matt finishes to suit your graphic needs. AUTO Wrap 1D Laminate is rated for outdoor durability up to 5 years.

APPLICATIONS & FEATURES

- Suitable for use with AUTO Wrap 1D Film.
- Intermediate interior & exterior signage.
- UV inhibitors to protect and extend the life of your printed graphics.
- AUTO Wrap overlaminate film is designed to be laminated cold without any heat.

ADHESIVE

Permanent (Clear).

RELEASE LINER

Clay Coated.

RECOMMENDED PRINT FILMS:

- AUTO Wrap 1D Film.

OPTIMUM PERFORMANCE:

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility. AUTO Wrap 1D Laminate will resist weathering best when applied to vertical or upper outboard angles. Horizontal angles, such as hood and auto roof surfaces, will deteriorate more quickly than vertical. This is due to increased exposure to sun and moisture, as well as continued high deposition of dirt and atmospheric contaminants. AUTO Wrap does not recommend its film for horizontal or close horizontal applications.

PRINTING CONSIDERATIONS:

- It is important to allow ink to dry as much as possible before laminating or application (min. 24h).
- The outgassing time depends on different factors such as the printer, ink load, environment temperature, humidity level, air circulation, product wetness, and drying method.
- Use matched component laminates.
- Work area immediately around the printer is dust and dirt free.
- The printing areas should be in clean and temperature controlled area.

Technical Data

Surface finish	80 to 90 Gloss Units (Gloss)
Gloss Meter 60° Reflection	10 to 15 Gloss Units (Matt)
Thickness ⁽¹⁾	80 microns
Peel adhesion	≥ 0.39 kg/cm
Dimensional stability ⁽¹⁾	≤ 0.63 mm
Service temperature ⁽²⁾	-29°C to 65°C
Tensile strength	1.8 kg/cm
Elongation at break	≥ 150%
Shelf life ⁽³⁾	1 year from factory shipment
Application temperature	15°C to 26°C
Available width	137.2 cm 152.4 cm
Liner release	≤ 12 g/cm
Maximum service life by specialist application	5 years
Applies for vertical outdoor exposure ⁽⁴⁾	

(1) average (2) short-term exposure (3) in original packaging, at 20° C and 50% relative humidity (4) maximum service life when applied by a specialist, and with the proper maintenance and care. Vertical outdoor weathering and central European climate. The actual and expected service life is determined by the environmental conditions, as well as pre-treatment of the substrate and regular maintenance

APPLICATION GUIDELINE:

Whether laminating lined overlaminating film using a laminating machine it is critical to use only as much unwind tension and nip pressure (gap closure) as needed to create a bubble and wrinkle free laminate. Excess lamination tension causes a variety of downstream problems with handling, installation and even after installation. When material emerges from the lamination process it should lay as flat as when it went in.



MAINTENANCE GUIDELINE:

- 3 days after application: cleaning in car wash is possible.
- No high pressure cleaning recommended.
- For long-lasting film properties we recommend to regularly use cleaning and care products.

POST-CARE & CLEANING INSTRUCTIONS:

"Fleet graphics bundles can be easily cleaned using a pressure washer but can be damaged just as easily by improperly handling the water spray or incorrectly blending the cleaning solutions. Regular washing is highly recommended to avoid the necessity of deep cleaning and to prevent accumulating dirt. In order to keep the film from degrading or lifting around the edges while pressure washing, it is important to adhere to the following guidelines:

1. Nozzle pressure should never exceed 1,300 PSI.
2. Water temperature should never exceed 140°F (60°C).
3. Nozzle tip should never be closer than five feet from the graphics.
4. Angle of water spray should be no shallower than 60° from perpendicular. Keep the nozzle spray pattern perpendicular to the overlapping direction.
5. Detergent solutions should always be blended with water at the correct ratio and pH (between 6 and 8). A more concentrated solution can damage both the adhesive and film.
6. A post-washing, fresh-water rinse will help maintain the life of the paint and film.

IMPORTANT TO NOTE:

The information in this datasheet is based upon our present knowledge and practical experience. The information is given without any guarantee or agreement with regards to the quality or properties of the material. It does not constitute a warranty of any certain quality, properties and/or service life concerning the AUTO SE colour films. Please note that by nature films are more sensitive than lacquers. Therefore, films must be treated and maintained with the greatest care. For application of colour films (wrapping and removal) as well as for maintenance and use, please refer to our documents 'Processing Guidelines'. If our guidelines are not followed, please be advised that in particular the maximum service life information, stated as based on our experience, does not apply and any warranty and liability is excluded.

REMOVABILITY GUIDELINE:

1. Heat the area to be removed evenly with your heat source to approximately 125°F (50°C). In some climates the sun will give sufficient heat to do this. If temperatures exceed 125°F (50°C) the film may delaminate leaving the adhesive behind making the removal much more difficult.
2. Gently lift the edge of the graphic. When you have removed enough to get a good hand hold, begin lifting the graphic by pulling away from the vehicle at a 15° angle. Do not pull the film away from the vehicle at an angle greater than 90° as this will cause the film to delaminate leaving the adhesive behind.
3. Try to keep the leading edge of the removal in a straight line by spreading your fingers out along the top of the removed graphic. Pull slowly for a clean removal.

APPLICATION TRAINING:

Training & education is the key to success a perfect installation. Spandex offers regular training for customers interested in application courses. Please contact your local Spandex for more information.

NOTE: Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. We also recommend to test compatibility on raw & primed MDO prior to installation due to variation in substrate properties. Furthermore, the application information published by AUTO must be considered.

IMPORTANT NOTICE: All AUTO products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning AUTO products is based upon research which the company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of AUTO products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

DISCLAIMER GENERAL: Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of such products for their specific use, including, but not limited to, the application, conditions, maintenance, and the Purchaser shall assume all risk and liability of every nature in connection therewith. All technical data are subject to change without prior notice. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading. Spandex gives no express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of fitness for any particular use and/or non-infringement. All products are sold subject to Spandex's general terms and conditions of sale. Spandex's aggregate liability, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoiced to Purchaser in respect of any occurrence or series of occurrences. In the event of improper use and/or incorrect processing that does not comply with our instructions, any and all liability is excluded. In no circumstances shall Spandex be liable for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.