Matt White Film

 $120\mu/4.7$ mil 2-side matt aqueous coated polyester film, optimised for dry toner print applications.

Property	Typical Value	Unit	Test Method
Total Thickness	118 +/- 4	μ	Electronic micrometer
Weight	160 +/- 5	g/m²	Internal method
Opacity	>96	%	TAPPI T519
CIE Whiteness	>140	CIE WI	ASTM E313 DCI Spectraflash (D65, 10° observer, UV incl.)
Gloss 60°	<4	%	BYK Gardner
Shrinkage	MD -0.37 TD + 0.1	%	5 minutes @ 150°C (297mm length)
Tensile Strength	MD 14 TD 17	kgF/mm²	ASTM D882-83
Elongation at break	MD 120 TD 120	%	ASTM D882-83
Melting Point	250	°C	ASTM E794-85

- · Matt white opaque suitable for full colour duplex printing
- · Waterproof, tear-proof, greaseproof, can be hole punched
- Great for presentation covers & signs
- · No need to laminate

Compatibility Guidance

Suitable for most thermal transfer and dry toner (laser/LED/flash fusion) print processes, both mono and colour small-volume, mid-volume & production machines.

On such machines the user must establish for themselves the optimum settings and paper path, being aware of the thickness and weight of the material.

Recommended Conditions

Printroom	10°C - 30°C	40% - 55% RH
Usage	-40°C - 120°C	10% - 100% RH
Storage	10°C - 20°C	20% - 55% RH

Please return unused product to its original packaging

Shelf Life: 24 months after delivery (under recommended storage conditions)